

Properties	Unit	Test method	Values
Polymer base			SEBS
Colour			Translucent
Hardness	Sh A	ISO 868 (3s)	45
Tensile strength	MPa	ISO 37	↔ 6,12
Elongation at break	%	ISO 37	↔ 700
Density	g/cm <sup>3</sup>	ISO 1183-1	0,9
Tear resistance	N/mm	ISO 34-2	↓21 ↔ 20
Compression set 22h/23 °C	%	ISO 815-1 A	55
Compression set 22h/70 °C	%	ISO 815-1 A	30

#### Special properties

Adhesion to PP  
Excellent compression set  
Sterilizable: Ethylene Oxide, gamma radiation (2 x 35 kGy)

#### Applications

Medical and pharmaceutical  
Flexible connections  
Seals, mouthpieces, soft touch, valves

#### Caution

All values reported are typical values based on sample laboratory tests and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer.

Fire may create small amounts of hydrogen sulfide and carbon dioxide. Disposal by incineration in compliance with local regulations.