

Properties	Unit	Test method	Values
Polymer base			SEBS
Colour			Black
Hardness	Sh A	ISO 868 (3s)	80
Tensile strength	MPa	ISO 37	↔612
Elongation at break	%	ISO 37	↔700
Density	g/cm ³	ISO 2718	0,9
Tensile modulus at 100% elongation	MPa	ISO 37	↔2,7
Tensile modulus at 200% elongation	MPa	ISO 37	↔3,6

Special properties	Applications
Food contact	Food contact

Caution

All values reported are typical values based on sample laboratory tests and are not a guarantee of performance. The responsibility to conduct testing to determine suitability of use for the particular process or end-use application remains with the customer.

Fire may create small amounts of hydrogen sulfide and carbon dioxide. Disposal by incineration in compliance with local regulations.